

MICRO-AIR®

Admixture for entraining air in concrete

DESCRIPTION:

MICRO-AIR® air-entraining admixture provides concrete with extra protection by creating ultrastable air bubbles that are strong, small and closely spaced—a characteristic especially useful in the types of concrete known for their difficulty to entrain and maintain the air content desired.

Even when used at a lower dosage rate than standard air-entraining admixtures, MICRO-AIR meets the requirements of ASTM C 260, AASHTO M 154, CRD-C 13 and other Federal and State specifications.

ADVANTAGES OF AIR ENTRAINMENT:

The entrainment of optimum air content in concrete results in the following improvements in concrete quality:

- Increased resistance to damage from freeze/thaw cycles and to scaling from deicing salts¹
- Reduced permeability—increased watertightness
- Reduced segregation and bleeding
- Improved plasticity and workability

¹Concrete durability research has established that the best protection for concrete from the adverse effects of freeze/thaw cycles and deicing salts results from: • proper air content in the hardened concrete; • a suitable air-void system in terms of bubble size and spacing; and • adequate concrete strength, assuming the use of sound aggregates and proper mixing, placing, handling and curing techniques.

When unusually low or high amounts of an air-entraining admixture are required to achieve normal ranges of air content or if the required amount of air-entraining admixture necessary to achieve required levels of air content is observed to change significantly under given conditions, the reason should be investigated. In such cases, it is especially important to determine: (a) that a proper amount of air is contained in the fresh concrete at the point of placement; and (b) that a suitable air-void system (spacing factor) is being obtained in the hardened concrete.

ADVANTAGES OF MICRO-AIR:

- Greatly improved stability of air-entrainment
- Improved air-void system in hardened concrete
- Improved ability to entrain and retain air in low-slump concrete; concrete containing high-carbon content fly ash; concrete containing large amounts of fine materials; concrete using high-alkali cements; high-temperature concrete; and concrete with extended mixing times

FEATURES/BENEFITS:

Ready to Use—Solution is the proper concentration for rapid, accurate dispensing.

Compatible for Use—MICRO-AIR admixture is compatible with concrete containing other admixtures—water-reducers, high-range water-reducers, accelerators, retarders, and water repellents.

The use of MICRO-AIR air-entraining admixture with Master Builders water-reducing, set-controlling admixtures forms a desirable combination for producing the highest quality, normal or lightweight concrete. Heavyweight concrete normally does not contain entrained air.

NOTE: As stated in ACI 212 and other publications, when two or more admixtures are used, they must be added to the mix separately (through dispensers or manually) and must not be mixed with each other prior to adding to the concrete mix.

For optimum, consistent performance, the air-entraining admixture should be dispensed on damp, fine aggregate or with the initial batch water. When using lightweight aggregate, field evaluations should be conducted to determine the best method to dispense the air-entraining admixture.

USAGE INFORMATION:

Add MICRO-AIR admixture to the concrete mix using a dispenser designed for air-entraining admixtures; or add manually using a suitable measuring device that ensures accuracy within plus or minus 3% of the required amount.

Measure the air content of the trial mix and either increase or decrease the quantity of MICRO-AIR admixture to obtain the desired air content in the production mix. Check the air content of the first batch and make further adjustments if needed. Due to possible changes in the factors that affect the dosage rate of MICRO-AIR, frequent checks should be made during the course of the work. Adjustments to the dosage should be based on the amount of entrained air in the mix at the point of placement.

QUANTITY TO USE:

There is no standard dosage rate for MICRO-AIR admixture. The exact quantity of air-entraining admixture needed for a given air content of concrete is not predictable because of differences in concrete making materials. Typical factors which might influence the amount of air entrained are: temperature, cement, sand grading, mix proportions, slump, means of conveying and placement, use of extra fine materials such as fly ash, etc.

The amount of MICRO-AIR admixture used will depend upon the amount of entrained air required under actual job conditions. In a trial mix, use 1/8 to 1-1/2 fl oz/100 lb (8 to 98 mL/100 kg) of cement. In mixes containing water-reducing, set-controlling admixtures, the amount of MICRO-AIR needed is somewhat less than the amount required in plain concrete. In mixes requiring a higher or lower dosage to obtain the desired air content, consult your local Master Builders representative.

AIR CONTENT DETERMINATION:

The total air content of normal weight concrete should be measured in strict accordance with ASTM C 231, "Standard Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method" or ASTM C 173, "Standard Test Method for Air Content of Freshly Mixed Concrete by the Volumetric Method." The air content of lightweight concrete should only be determined using the Volumetric Method.

The air content should be verified by calculating the gravimetric air content in accordance with ASTM C 138, "Unit Weight, Yield, and Air Content (Gravimetric) of Concrete." If the total air content, as measured by the Pressure Method or Volumetric Method and as verified by the Gravimetric Method, deviates by more than 1-1/2%, the cause should be determined and corrected through equipment calibration or by whatever process is deemed necessary.

TEMPERATURE PRECAUTION:

MICRO-AIR admixture should be stored and dispensed at 35 °F (2 °C) or higher. Although freezing does not harm this product, precautions should be taken to protect it from freezing. If it freezes, thaw and reconstitute by mild mechanical agitation. Do not use pressurized air for agitation.

PACKAGING:

MICRO-AIR admixture is supplied in 55 U.S. gallon (208 liter) drums and bulk delivery.

CAUTION:

MICRO-AIR admixture is a CAUSTIC solution. Chemical goggles and gloves are recommended if transferring or handling large quantities of material. (See MSDS and/or product label for complete information.)

NON-CHLORIDE, NON-CORROSIVE:

MICRO-AIR admixture will not initiate or promote corrosion of reinforcing steel embedded in concrete, prestressed concrete or concrete placed on galvanized steel floor and roof systems. Calcium chloride is not an added ingredient in the manufacture of MICRO-AIR admixture. Based on the chlorides originating from all ingredients used in manufacture, MICRO-AIR admixture contributes less than 0.0001% (1.0 ppm) chloride ions by weight of the cement when used at the rate of 1 fl oz per 100 lb (65 mL per 100 kg) of cement.

For suggested specification information or for additional product data on MICRO-AIR air-entraining admixture, contact your local Master Builders representative.

Master Builders, Inc. United States

23700 Chagrin Boulevard
Cleveland, Ohio 44122-5554
(800) MBT-9990
Fax (216) 831-6910

Canada

3637 Weston Road
Toronto, Ontario M9L 1W1
(800) 387-5862
Fax (416) 741-7925

Mexico

Blvd. M. Avila Camacho 80, 3er Piso
53390 Naucalpan, México
011-525-557-5544
Fax 011-525-395-7903