

MASTERKURE® CR (COLORS)

Colored curing compound and maintenance sealer for concrete

DESCRIPTION:

MASTERKURE CR (COLORS) concrete curing compound and maintenance sealer is available in a variety of colors. Designed for interior and exterior use on colored concrete floors only, MASTERKURE CR (COLORS) helps ensure that maximum strength, greater wear resistance and minimum dusting are achieved.

This product meets the moisture-retention requirements of ASTM C-309, "Specifications for Liquid Membrane-Forming Compounds for Curing Concrete," when applied at 350 ft²/gallon (8.6 m²/liter).

MASTERKURE CR (COLORS) can also be used as a maintenance sealer for existing concrete floors when used at an application rate of 500 ft²/gallon (12.3 m²/liter).

RECOMMENDED FOR:

- Curing concrete floors finished with the corresponding color formulation of MASTERPLATE® 200, MASTERCRON LR® or COLORCRON® floor hardener
- Use as part of an ongoing maintenance program for a MASTERPLATE 200, MASTERCRON LR or COLORCRON floor of the same color
- Use where the slipperiness of a colored floor wax makes it undesirable for use as a maintenance product

FEATURES/BENEFITS:

- Proper and efficient curing of colored floors
- Provides an even-colored floor surface
- With proper preparation, it can be used as a dress-up maintenance sealer to make sweeping and cleaning easier
- Does not freeze
- Available in the following colors:

Tile Red

Terra Cotta

French Gray

Nile Green

Light Reflective

Battleship Gray

PACKAGING/ESTIMATING:

MASTERKURE CR (COLORS) curing compound and maintenance sealer is packaged in 5 gallon (19 liter) metal pails.

One gallon will cover approximately 350 ft² (8.6 m²/liter).

APPLICATION:

Mix MASTERKURE CR (COLORS) in the pail to ensure that the pigment is properly distributed. If the product is allowed to sit in the pail for more than 20 minutes, remix. Use a mechanical mixer. DO NOT mix by hand.

For Maintenance Sealing: If using reapplications of this product for maintenance purposes, thoroughly clean the surface receiving the application. All grease, oil, dirt or any other type of surface contamination must be removed and the surface allowed to dry prior to applying MASTERKURE CR (COLORS). Once the surface will not be marred by its application, apply a thin coat of MASTERKURE CR (COLORS) with a constant sprayer or a short nap roller at the rate of 500 ft²/gallon (12.3 m²/liter).

Note: DO NOT overlap applications. DO NOT add thinner. If a second **thin** application is desired, the first coat must be allowed to dry for 24 hours before the second coat is applied.

Drying time is approximately 1 to 3 hours at 70 °F (21 °C). When dry, the treated surface is nontracking.

For cleaning the product from spray equipment or rollers, use solvents (KB 80 or higher) such as aromatic naphtha, xylene or toluene. These solvents are flammable so proper caution should be exercised, including ventilation.

LIMITATIONS:

- DO NOT USE:
 - For extra heavy-duty traffic environments on colored floors.
 - Where any chemical resistance is needed i.e. (exposure to hydrocarbon solvents, thinners and hydraulic fluids).
 - Where the need to remove the product at any future time is anticipated.
 - For coloring plain concrete or natural colored dry shakes or toppings.
- Always thoroughly mix product before using and remix at least every 20 minutes.
- Thick or uneven applications of MASTERKURE CR (COLORS) sealer may cause the surface to have a mottled appearance.
- MASTERKURE CR (COLORS) sealer is combustible, therefore keep it away from heat and flame.
- Use only with adequate ventilation.
- When applying this material, the use of a NIOSH approved, organic vapor respirator is recommended.
- Avoid prolonged contact with skin or breathing of vapors.
- Keep container tightly closed at all times when product is not in use.
- Keep product out of the reach of children.
- Do not apply to surfaces that are wet.

RELATED BULLETINS:

Material Safety Data Sheet – MASTERKURE CR (COLORS)

Master Builders, Inc. United States

23700 Chagrin Boulevard
Cleveland, Ohio 44122-5554
(800) MBT-9990
Fax (216) 831-6910

Canada

3637 Weston Road
Toronto, Ontario M9L 1W1
(800) 387-5862
Fax (416) 741-7925

Mexico

Blvd. M. Avila Camacho 80, 3er Piso
53390 Naucalpan, México
011-525-557-5544
Fax: 011-525-395-7903