

**PITTSBURGH PAINTS**A new generation of paint company  
for a new generation.**SPEEDHIDE®****6-411 Series****Architectural Coatings****SPEEDHIDE® Interior Enamel Eggshell Latex****Generic Type**

Vinyl Acrylic Latex

**Tinting and Base Information**

Use PITTSBURGH® Paints Custom Colorants to achieve hundreds of colors. Refer to THE VOICE OF COLOR® electronic CD or formula book for tinting instructions.

6-411	White and Pastel Base
6-415	Midtone Base
6-416	Deeptone Base
6-417	Neutral Base

**General Description**

Our best professional interior latex formulated to meet the performance requirements of professional applicators. SPEEDHIDE® Interior Eggshell Latex is designed as a high hiding product with excellent touch-up ability when applied by brush, roller or spray. The quick dry allows faster recoat and provides a uniform, washable eggshell finish on interior walls, ceilings and trim surfaces. Recommended for use on properly prepared plaster, wallboard, wallpaper (without metallic design), masonry, wood and metal surfaces.

**Recommended Uses**

Masonry  
Primed Metal  
Wallpaper (without metallic design)  
Wallboard  
Walls  
Ceilings  
Wood Trim

**Features / Benefits**

High Hiding  
Excellent Touch-Up Properties  
Scrubbable  
Soap & Water Clean-Up  
Available in More Than 1800 Colors from THE VOICE OF COLOR® Design Collection

**Limitations of Use**

Apply when air, surface or product temperatures are above 50°F (10°C). Protect from freezing. Not recommended for use on floors.

**Product Data**

<b>Gloss:</b>	Eggshell: 4 to 8 (60° Gloss Meter)
<b>VOC*:</b>	0.62 lbs/gal (74.40 g/L)
<b>DFT:</b>	1.00 minimum to 1.30 maximum mils
<b>Coverage:</b>	400 to 500 sq. ft./gal. (37 to 46 sq. m/3.78L)

Note: Does not include loss due to varying application method, surface porosity, or mixing.

<b>Volume Solids*</b>	32% +/- 2.0%
<b>Weight Solids*</b>	46% +/- 2.0%
<b>Viscosity:</b>	95 to 105 KU
<b>Weight/Gallon:</b>	10.7 lbs. (4.8 kg) +/- 0.2 lbs. (91 g)
<b>Cleanup*:</b>	Soap and Water

\*Product data calculated on product 6-411.

**Drying Time:**

To Touch:	1 hours
To Handle:	2 hours
To Recoat:	4 hours
To Full Cure:	30 days

Dry Time @77°F (25°C); 50% relative humidity

**Flash Point:** Over 200°F, (93°C)

## Architectural Coatings

## SPEEDHIDE® Interior Enamel Eggshell Latex

## General Surface Preparation

Surface to be painted must be clean, dry, smooth, and free from dirt, grease, powdery or peeling paint, and other surface contaminants. All cracks and other surface imperfections must be repaired using high quality patching compounds, then allowed to dry thoroughly. Repaired areas should be sanded smooth and then spot-primed. Slick or glossy surfaces of previously applied paint, in sound condition, must be dulled by sanding.

Prime all bare wood, plaster, masonry, metal, patched and porous surfaces with the appropriate primer.

**NEW WOOD:** New wood should be sanded smooth and wiped clean. Any knots or resinous areas should be sealed before painting. Countersink all nails. Putty flush with surface, then prime.

**NEW PLASTER:** Fresh plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

**CONCRETE BLOCK, CINDER BLOCK, VERTICAL MASONRY:** New concrete should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-base paint must be prepared with extra care. Such coatings must be completely removed for best results. If the coatings appear to be adhering tightly, a masonry sealer may be applied to seal the surface prior to topcoating. One way to check adhesion is by applying a piece of masking tape. If it peels off easily and has loose particles adhering to it, remove all the chalking or crumbling material before repainting.

**METAL:** Rust and other surface contaminants must be removed from ferrous metals, aluminum, copper, brass, and galvanized steel. Then the surface must be cleaned thoroughly to remove any dust.

**GALVANIZED STEEL:** Caution must be used when selecting coatings for use on all galvanized metal surfaces. These substrates may have a factory-applied stabilizer, which is used to prevent white rusting during storage and shipping. Such stabilizers must be removed by either brush blasting or chemical treatment.

**WATER-SOLUBLE STAINS:** Apply SEAL-GRIP® Primer 17-21 or 17-31, over stained area prior to coating, to avoid bleeding of the stain into the topcoat.

## Recommended Primers

Galvanized Steel	6-209, 90-712
Ferrous Metal	6-208, 6-212, 90-712
Aluminum	6-204, 90-712
Gypsum Wallboard-Drywall	6-2, 17-21
Plaster	6-603
Brass	6-204, 90-712
Copper	6-204, 90-712
Concrete Masonry Units, Masonry (Block Fillers)	6-7, 6-12
Concrete, Masonry (Primers, Sealers)	6-603, 6-808
Wood	6-855, 6-6, 17-21

## Directions for Use

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, mix together (box) before applying. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

## Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 100°F	10 to 38°C
Substrate	50 to 100°F	10 to 38°C

PPGAF believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.

## Application Information

## Recommended Spread Rates:

Wet Mills :	3.2 minimum to	4.0 maximum
Wet Microns:	81.3 minimum to	101.6 maximum
Dry Mills :	1.0 minimum to	1.3 maximum
Dry Microns:	25.4 minimum to	33.0 maximum

**Application Equipment:** Apply with a high quality brush, paint pad, or by spray equipment.

**Airless Spray:** Pressure 2000 psi, tip 0.015" - 0.021"

**Brush:** Polyester/Nylon Brush

**Roller:** 3/16" - 3/8" nap roller cover

## Thinning:

No thinning is usually required. If necessary add up to 1/4 pint (118 mL) of water per gallon (3.78 L) of paint.

**Packaging:** 1-Gallon (3.78L)  
5-Gallon (18.9L)

Not all products are available in all sizes.



**PITTSBURGH PAINTS**  
A new generation of paint company  
for a new generation.

PPG Architectural Finishes, Inc.  
One PPG Place  
Pittsburgh, PA 15272

[www.pittsburghpaints.com](http://www.pittsburghpaints.com)

Technical Services:  
1-800-441-9695  
Architect/Specifier:  
1-888-774-7732  
International Sales:  
(412) 434-2049

PPG Coatings, Inc.  
Coatings and Resins Group  
5546 Timberlea Blvd.  
Mississauga, Ontario L4W2T7  
(905) 238-6441

**Bulletin: 6-411**

Additional copies of this bulletin can be obtained from our web site or by calling 1-800-428-7806.

Rev. 3/2000