

**PITTSBURGH® PAINTS**A new generation of paint company
for a new generation.**PITTSBURGH® Paints****19-510 Series****Architectural Coatings****PITTSBURGH® Paints Kitchen, Bath & Trim Semi-Gloss Enamel****Generic Type**

100% Acrylic Latex

General Description

Our premium interior semi-gloss acrylic is formulated to meet the performance requirements of the residential and commercial markets. The 100% acrylic technology and semi-gloss sheen allows PITTSBURGH® Paints Kitchen & Bath to be especially effective in high moisture and dirt-prone areas which require frequent washing and stain removal, like kitchens and bathrooms. It has excellent adhesion to aged alkyds and glossy surfaces. The quick dry time provides early moisture resistance on interior walls, ceilings, trim and counter tops. Recommended for use on properly prepared and primed or previously painted wallboard, cured plaster and masonry, wallpaper (without metallic design), wood and metal surfaces.

Recommended Uses

Dirt and Grease Prone Areas
Ceilings
Tops of Counters and Shelves
Kitchen and Bathroom Walls
Wood Trim

Features / Benefits

Excellent Hiding
Excellent Adhesion (especially to aged alkyds and glossy surfaces)
Excellent Stain Resistance
Excellent Scrubbability
Spatter Resistant
Non-Yellowing
Soap & Water Clean-Up
Available in More than 1,800 Colors in THE VOICE OF COLOR® Design Collection

Limitations of Use

Apply when air, surface and product temperatures are above 50°F(10°C). Protect from freezing. Not recommended for use on floors. Do not wash before 10 days to allow paint to cure properly. Do not wash with abrasive cleaners. If recoating after 72 hours, light sanding is recommended.

Tinting and Base Information

Use PITTSBURGH® Paints Custom Colorants and four bases to achieve hundreds of colors. Refer to THE VOICE OF COLOR® electronic CD or formula book for tinting instructions.

19-510	White and Pastel Base
19-515	Midtone Base
19-516	Deeptone Base
19-517	Neutral Base

Product Data

Gloss:	Semi-Gloss:40 to 60 (60°Gloss Meter)
VOC*:	0.89 lbs/gal (106.80 g/L)
DFT:	1.00 minimum to 1.20 maximum mils
Coverage:	400 to 500 sq. ft./gal. (37 to 46 sq. m/3.78L)

Note: Does not include loss due to varying application method, surface porosity, or mixing.

Volume Solids*	30% +/- 2.0%
Weight Solids*:	41% +/- 2.0%
Viscosity:	95 to 105 KU
Weight/Gallon:	10.0 lbs. (4.5 kg) +/- 0.2 lbs. (91 g)
Cleanup*:	Soap and Water

*Product data calculated on product 19-510.

Drying Time:

To Touch:	1 hour
To Handle:	1 hour
To Recoat:	2 hours
To Full Cure:	30 days

Dry Time @77°F (25°C); 50% relative humidity

Flash Point: Over 200°F, (93°C)

Architectural Coatings

PITTSBURGH® Paints Kitchen, Bath & Trim Semi-Gloss Enamel

General Surface Preparation

Surface to be painted must be clean, dry, smooth, and free from dirt, grease, powdery or peeling paint, and other surface contaminants. All cracks and other surface imperfections must be repaired using high quality patching compounds, then allowed to dry thoroughly. Repaired areas should be sanded smooth and then spot-primed. Slick or glossy surfaces of previously applied paint, in sound condition, must be dulled by sanding.

Prime all bare wood, plaster, masonry, metal, patched and porous surfaces with the appropriate primer.

NEW WOOD: New wood should be sanded smooth and wiped clean. Any knots or resinous areas should be sealed before painting. Countersink all nails. Putty flush with surface, then prime.

NEW PLASTER: Fresh plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

CONCRETE BLOCK, CINDER BLOCK, VERTICAL MASONRY: New concrete should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-base paint must be prepared with extra care. Such coatings must be completely removed for best results. If the coatings appear to be adhering tightly, a masonry sealer may be applied to seal the surface prior to topcoating. One way to check adhesion is by applying a piece of masking tape. If it peels off easily and has loose particles adhering to it, remove all the chalking or crumbling material before repainting.

METAL: Rust and other surface contaminants must be removed from ferrous metals, aluminum, copper, brass, and galvanized steel. Then the surface must be cleaned thoroughly to remove any dust.

GALVANIZED STEEL: Caution must be used when selecting coatings for use on all galvanized metal surfaces. These substrates may have a factory-applied stabilizer, which is used to prevent white rusting during storage and shipping. Such stabilizers must be removed by either brush blasting, sanding or chemical treatment.

WATER-SOLUBLE STAINS: Apply SEAL-GRIP® Primer 17-21 or 17-31, over stained area prior to coating, to avoid bleeding of the stain into the topcoat.

Recommended Primers

Wood	6-855, 6-6, 17-21
Gypsum Wallboard-Drywall	6-2, 17-21
Aluminum	6-204, 90-712
Ferrous Metal	6-208, 6-212, 90-712
Galvanized Steel	6-209, 90-712
Concrete Masonry Units, Masonry (Block Fillers)	6-7, 6-12
Plaster	6-603
Brass	6-204, 90-712
Copper	6-204, 90-712
Concrete, Masonry (Primers, Sealers)	6-603, 6-808

Directions for Use

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, mix together (box) before applying. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 100°F	10 to 38°C
Substrate:	50 to 100°F	10 to 38°C

PPGAF believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.

Application Information

Recommended Spread Rates:

Wet Mills :	3.2 minimum to	4.0 maximum
Wet Microns:	81.2 minimum to	101.6 maximum
Dry Mills :	1.0 minimum to	1.2 maximum
Dry Microns:	25.4 minimum to	30.4 maximum

Application Equipment: Apply with a high quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat.

Airless Spray: Pressure 2000 psi, tip 0.015" - 0.021"

Brush: Polyester/Nylon Brush

Roller: 3/16" - 3/8" nap roller cover

Thinning:

No thinning is usually required. If necessary add up to 1/4 pint (118 mL) of water per gallon (3.78 L) of paint.

Packaging: 1-Gallon (3.78L)
Quart (946 mL)

Not all products are available in all sizes.



PITTSBURGH PAINTS
A new generation of paint company
for a new generation.

PPG Architectural Finishes, Inc.
One PPG Place
Pittsburgh, PA 15272

www.pittsburghpaints.com

Technical Services:
1-800-441-9695
Architect/Specifier:
1-888-774-7732
International Sales:
(412) 434-2049

PPG Coatings, Inc.
Coatings and Resins Group
5546 Timberlea Blvd.
Mississauga, Ontario L4W2T7
(905) 238-6441

Bulletin: 19-510

Additional copies of this bulletin can be obtained from our web site or by calling 1-800-428-7806.

Rev. 3/2000