



Architectural Coatings

SPEEDHIDE® Exterior Latex Masonry Surface Sealer

Generic Type

Tinting and Base Information

Acrylic Latex

DO NOT TINT.
6-808 Clear

General Description

SPEEDHIDE® Exterior Latex Masonry Surface Sealer is formulated for use as a seal coat on weathered, chalky, and porous masonry surfaces (porous brick, cement board, low density concrete products) to rebind the chalky residue to the substrate before painting. Recommended for use on properly prepared cement board, low density concrete, brick and cured masonry.

Recommended Uses

- Brick
- Cement Board
- Low Density Concrete
- Masonry

Features / Benefits

- Excellent Adhesion
- Re-binds Chalk to the Substrate
- Fast Dry and Re-coat
- Soap & Water Clean-Up

Limitations of Use

Apply when air, surface and product temperatures are above 50°F (10°C) and surface temperature is at least 5°F (3°C) above the dew point. Avoid painting late in the day when dew and condensation are likely to form or if rain is threatening. Protect from freezing. Not for use as a topcoat or for immersion service. Apply one coat at 2 1/2 - 3 mils wet film. Do not apply heavy films. two coats may be required on chalky or extremely porous surfaces.

Product Data

- Gloss:** Clear
- VOC*:** 0.53 lbs/gal (64.00 g/L)
- DFT:** 0.30 minimum to 0.40 maximum mils
- Coverage:** 535 to 640 sq. ft./gal. (50 to 60 sq. m/3.78L)
- Note: Does not include loss due to varying application method, surface porosity, or mixing.
- Volume Solids*:** 13.5% +/- 2.0%
- Weight Solids*:** 15.1% +/- 2.0%
- Viscosity:** 10 to 20 sec. #4 Ford Cup
- Weight/Gallon:** 8.5 lbs. (3.9 kg) +/- 0.2 lbs. (91 g)
- Cleanup*:** Soap and Water

*Product data calculated on product 6-808.

Drying Time:

- To Touch: 30 minutes
- To Handle: 1 hour
- To Recoat: 4 hours
- To Full Cure: 4 hours

Dry Time @77°F (25°C); 50% relative humidity

Flash Point: Over 200°F, (93°C)

Architectural Coatings

SPEEDHIDE® Exterior Latex Masonry Surface Sealer

General Surface Preparation

Surface must be clear and free of dirt, grease, wax, mildew and flaking paint. Remove wax and grease with a high quality paint thinner. Remove peeling, flaking, loose paint, excess chalk, and efflorescence by wire brushing, scraping, sanding or pressure washing. Surfaces previously coated with water thinned cement-base paint must be prepared with extra care. Such coatings must be completely removed for best results. If the coatings appear to be adhering lightly, this masonry sealer may be applied to seal the surface prior to topcoating. Remove and inhibit regrowth of mildew by using MILDEW CHECK® Multi-Purpose Wash, 18-1, by PITTSBURGH® Paints. Before use, be sure to read and follow the instructions and warnings on the label.

Recommended Primers

none

Refer to Surface Preparation Recommendations.

Application Information

Recommended Spread Rates:

Wet Mills :	2.5 minimum to	3.0 maximum
Wet Microns:	63.5 minimum to	76.2 maximum
Dry Mills :	0.3 minimum to	0.4 maximum
Dry Microns:	7.6 minimum to	10.2 maximum

Application Equipment: Apply with high quality brush, roller, paint pad or by spray equipment.

Airless Spray: Pressure 1000 psi, tip 0.011" - 0.017"

Brush: Polyester/Nylon Brush

Roller: 3/8" - 3/4" nap roller cover.

Thinning:

Thinning is not recommended.

Directions for Use

Hand stir thoroughly. Must be back-brushed if spray applied. Read all label and Material Safety Data Sheet (MSDS) label information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 100°F	10 to 38°C
Substrate	50 to 100°F	10 to 38°C

PPGAF believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.

Packaging: 1-Gallon (3.78L)
5-Gallon (18.9L)

Not all products are available in all sizes.



PITTSBURGH PAINTS
A new generation of paint company
for a new generation.

PPG Architectural Finishes, Inc.
One PPG Place
Pittsburgh, PA 15272

www.pittsburghpaints.com

Technical Services:
1-800-441-9695
Architect/Specifier:
1-888-774-7732
International Sales:
(412) 434-2049

PPG Coatings, Inc.
Coatings and Resins Group
5546 Timberlea Blvd.
Mississauga, Ontario L4W2T7
(905) 238-6441

Bulletin: 6-808

Additional copies of this bulletin can be obtained from our web site or by calling 1-800-428-7806.

Rev. 3/2000