

**Architectural Coatings****SPEEDPRO® Interior/Exterior Flat Latex****Generic Type**

Vinyl Acrylic Latex

Tinting and Base Information

Use PITTSBURGH® Paints Custom Colorants to achieve many white and pastel colors. Refer to THE VOICE OF COLOR® electronic CD or formula book for tinting instructions.

14-650

White and Pastel Mixing Base

General Description

Our professional quality paint formulated to be used in commercial markets where application speed and good quality are needed. SPEEDPRO® Interior/Exterior Flat Latex provides a uniform, flat finish on properly prepared and primed or previously painted interior and exterior surfaces of wood, metal, brick, cement block, wallboard, cured concrete, plaster, stucco and masonry surfaces.

Recommended Uses

Drywall
Masonry
Plaster
Primed Metal
Wood

Features / Benefits

Good Hiding
Uniform, Flat Finish
Easy Application
Soap & Water Clean-Up

Limitations of Use

Apply when air, surface and product temperatures are above 50°F (10°C), and surface temperature is at least 5°F (3°C) above the dew point. Avoid exterior painting late in the day when dew and condensation are likely to form or if rain is threatening. Protect from freezing. Not recommended for use on floors.

Product Data

Gloss: Flat: 0 to 5 (60° & 85° Gloss Meter)
VOC*: 0.81 lbs/gal (97.00 g/L)
DFT: 0.80 minimum to 1.00 maximum mils
Coverage: 400 to 500 sq. ft./gal. (37 to 46 sq. m/3.78L)

Note: Does not include loss due to varying application method, surface porosity, or mixing.

Volume Solids*: 24% +/- 2.0%
Weight Solids*: 41.2% +/- 2.0%
Viscosity: 90 to 100 KU
Weight/Gallon: 10.9 lbs. (4.9 kg) +/- 0.2 lbs. (91 g)
Cleanup*: Soap and Water

*Product data calculated on product 14-650.

Drying Time:

To Touch: 30 minutes
To Handle: 1 hour
To Recoat: 4 hours
To Full Cure: 30 days

Dry Time @77°F (25°C); 50% relative humidity

Flash Point: Over 200°F, (93°C)

Architectural Coatings

SPEEDPRO® Interior/Exterior Flat Latex

General Surface Preparation

Surface to be painted must be clean, dry, and free of dirt, loose and peeling paint, mildew, chalk, grease, rust, and other surface contaminants. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Prime all bare wood, metal, and porous surfaces with the appropriate primer. On exterior surfaces, remove and inhibit regrowth of mildew by using MILDEW CHECK Multi-Purpose Wash, 18-1, by PITTSBURGH Paints. Before use, be sure to read and follow the instructions and warnings on the label.

NEW WOOD: New wood should be sanded smooth and wiped clean. Any knots or resinous areas should be sealed before painting. Countersink all nails. Putty flush with surface, then prime.

PREVIOUSLY PAINTED SURFACES: All excessive chalking must be removed and the surface rinsed thoroughly. Remove all loose, peeling, or flaking paint by scraping or sanding. Feather back all rough edges to sound surface by sanding. Prime all bare wood areas.

CONCRETE BLOCK, CINDER BLOCK, VERTICAL MASONRY: New concrete should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-base paint must be prepared with extra care. Such coatings must be completely removed for best results. If the coatings appear to be adhering tightly, a masonry sealer may be applied to seal the surface prior to topcoating. One way to check adhesion is by applying a piece of masking tape. If it peels off easily and has loose particles adhering to it, remove all chalking or crumbling material before repainting.

METAL: Rust and other surface contaminants must be removed from ferrous metals, aluminum, copper, brass, and galvanized steel. Then the surface cleaned thoroughly to remove any dust.

GALVANIZED STEEL: Caution must be used when selecting coatings for use on all galvanized metal surfaces. These substrates may have a factory-applied stabilizer, which is used to prevent white rusting during storage and shipping. Such stabilizers must be removed by either brush blasting, sanding or chemical treatment.

WATER-SOLUBLE STAINS: Apply SEAL-GRIP® Primer 17-21 or 17-31, over stained area prior to coating, to avoid bleeding of the stain into the topcoat.

Recommended Primers

Gypsum Wallboard-Drywall	6-2, 17-21
Aluminum	6-204, 90-712
Ferrous Metal	6-208, 6-212, 90-712
Exterior Wood	6-809, 6-9, 6-609, 17-21
Concrete Masonry Units, Masonry (Block Fillers)	6-7, 6-12
Interior Wood	6-855, 6-6, 17-21
Galvanized Steel	6-209, 90-712
Plaster	6-603
Hardboard	17-21
Concrete, Masonry (Primers, Sealers)	6-603, 6-808

Directions for Use

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, mix together (box) before applying. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 100°F	10 to 38°C
Substrate:	50 to 100°F	10 to 38°C

PPGAF believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.

Application Information

Recommended Spread Rates:

Wet Mills :	3.2 minimum to	4.0 maximum
Wet Microns:	81.3 minimum to	101.6 maximum
Dry Mills :	0.8 minimum to	1.0 maximum
Dry Microns:	20.3 minimum to	25.4 maximum

Application Equipment: Apply with a high quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat.

Airless Spray: Pressure 2000 psi, tip 0.015" - 0.021"

Brush: Polyester/Nylon Brush

Roller: 3/8" - 3/4" nap roller cover.

Thinning:

No thinning is required.

Packaging: 1-Gallon (3.78L)
5-Gallon (18.9L)

Not all products are available in all sizes.



PITTSBURGH PAINTS
A new generation of paint company
for a new generation.

PPG Architectural Finishes, Inc.
One PPG Place
Pittsburgh, PA 15272

www.pittsburghpaints.com

Technical Services:
1-800-441-9695
Architect/Specifier:
1-888-774-7732
International Sales:
(412) 434-2049

PPG Coatings, Inc.
Coatings and Resins Group
5546 Timberlea Blvd.
Mississauga, Ontario L4W2T7
(905) 238-6441

Bulletin: 14-650

Additional copies of this bulletin can be obtained from our web site or by calling 1-800-428-7806.

Rev. 3/2000