

**Architectural Coatings****REZ® Interior Polyurethane Satin Varnish****Generic Type****Tinting and Base Information**

Oil Modified Urethane Resin

**DO NOT TINT.**

77-89 Satin

**General Description**

Our premium low VOC satin varnish polyurethane formulated to meet the performance requirements of the residential and commercial markets. REZ® Interior Polyurethane Gloss Varnish is an oil modified urethane based, clear coating that provides abrasion resistance on interior wood surfaces, including floors. Recommended for use on interior wood, wall paneling, doors, bar tops, wood cabinets and floors.

**Recommended Uses**

Doors  
Floors  
Cabinets  
Trim  
Furniture  
Wood

**Features / Benefits**

Excellent Adhesion  
Abrasion-Resistant  
Tough, Durable Urethane Formula  
Excellent Washability

**Limitations of Use**

Apply when air, surface and product temperatures are above 50°F (10°C). Do not attempt to use on prewaxed wood flooring. Follow flooring manufacturer's coating recommendations. Not recommended in situations characterized by high heat or presence of corrosive chemicals nor for heavy duty use on floors. Allow 48 hours before putting into service and floors 72 hours before putting into full service.

**Product Data**

**Gloss:** Satin: 20 to 40 (60°Gloss Meter)  
**VOC\*:** 3.65 lbs/gal (438.00 g/L)  
**DFT:** 1.00 minimum to 1.40 maximum mils  
**Coverage:** 500 to 700 sq. ft./gal. (46 to 65 sq. m/3.78L)

Note: Does not include loss due to varying application method, surface porosity, or mixing.

**Volume Solids\*:** 43.8% +/- 2.0%

**Weight Solids\*:** 53.4% +/- 2.0%

**Viscosity:** 30 to 45 sec. Ford #4 Cup

**Weight/Gallon:** 7.8 lbs. (3.6 kg) +/- 0.2 lbs. (91 g)

**Cleanup\*:** Leptyne Paint Thinner 21-263

\*Product data calculated on product 77-89.

**Drying Time:**

To Touch: 1- 2 hours

To Handle: 4 hours

To Recoat: 8 hours

To Full Cure: 24 hours

Dry Time @77°F (25°C); 50% relative humidity

**Flash Point:** 104°F, (40°C)

## Architectural Coatings

## REZ® Interior Polyurethane Satin Varnish

## General Surface Preparation

The surface must be dry and completely free from dirt, grease, and wax. Putty all nail holes, end-joints, and other openings to match the color of the wood. Sand surface to remove surface imperfections and glaze of old finish coats. To refinish surfaces in poor or questionable condition, completely remove the old finish and treat as for new wood. To insure proper adhesion when recoating over existing lacquer sealer, shellac, or lacquer type fillers, sand thoroughly with fine sandpaper, and remove all fines. Lightly sand or steel wool between coats. Use a tack cloth to remove the dust that is generated by sanding.

## Recommended Primers

none

Refer to Surface Preparation Recommendations.

## Directions for Use

Stir well but do not shake. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

## Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 100°F	10 to 38°C
Substrate:	50 to 100°F	10 to 38°C

PPGAF believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.

## Application Information

## Recommended Spread Rates:

Wet Mills :	2.3 minimum to	3.2 maximum
Wet Microns:	58.4 minimum to	81.3 maximum
Dry Mills :	1.0 minimum to	1.4 maximum
Dry Microns:	25.4 minimum to	35.6 maximum

**Application Equipment:** Apply product with a high quality natural bristle brush.

**Airless Spray:** Not Recommended

**Brush:** High Quality Natural Bristle Brush

**Roller:** Not Recommended.

**Thinning:**

DO NOT THIN.

**Packaging:** 1-Gallon (3.78L)  
Quart (946 mL)

Not all products are available in all sizes.



**PITTSBURGH PAINTS**  
A new generation of paint company  
for a new generation.

PPG Architectural Finishes, Inc.  
One PPG Place  
Pittsburgh, PA 15272

www.pittsburghpaints.com

Technical Services:  
1-800-441-9695  
Architect/Specifier:  
1-888-774-7732  
International Sales:  
(412) 434-2049

PPG Coatings, Inc.  
Coatings and Resins Group  
5546 Timberlea Blvd.  
Mississauga, Ontario L4W2T7  
(905) 238-6441

**Bulletin: 77-89**

Additional copies of this bulletin can be obtained from our web site or by calling 1-800-428-7806.

Rev. 3/2000