

Inlaid Commercial Vinyl Flooring								
	Physical Characteristics			Recommended Subfloors/Adhesives				
	Size	Gauge	Indentation resistance in pounds per sq. in.	Consult Azrock Information Manual [¶] for complete and detailed information				
				Concrete, suspended	Concrete, on grade [§]	Concrete, below grade [§]	APA Plywood suspended	APA Sturd-i-floor ^³
Series 8000	6' wide	Nominal thickness 0.085	125	Azrock Inlaid Commercial Vinyl Adhesive	Azrock Inlaid Commercial Vinyl Adhesive	Azrock Inlaid Commercial Vinyl Adhesive	Azrock Inlaid Commercial Vinyl Adhesive	Azrock Inlaid Commercial Vinyl Adhesive

^³ APA Sturd-I-floor constructed per APA Design/Construction Guide, Residential and Commercial, Form E30L revised.

[§] Moisture test recommended

[¶] All Azrock products should be maintained according to the recommended procedures outlined in current Domco Installation & Maintenance Manual.

Inlaid Commercial Vinyl Flooring		
U.S. & Canadian Government Specifications	Chemicals, Reagents, and Stains	
L-F-475 A(3), Type II, Grade A; Government Building Material Regulations CSA; A126.3-M1984 Type 2, Grade A, ASTM E-648 (NFPA-253) and ASTM E-84 (NFPA-255), with a flame spread rating of less than 75	Alcohols	
	Ethanol	No stain
	Methanol	No stain
	Butanol	No stain
	Isopropyl Alcohol	No stain
	Ketones and Aldehydes	
	Acetone	No stain
	Methyl Ethyl Acetone	No stain
	Cyclohexanone	No stain
	Formaldehyde 25 g./l.	No stain
	Esters	
	Ethyl Acetate	No stain
	Propyl Acetate	No stain
	Isopropyl Acetate	No stain
Ethylene glycol	No stain	
Acids		
Acetic Acid	Slight stain	
Sulphuric Acid 98%	Yellowing	
Sulphuric Acid 2N	Slight stain	
Nitric Acid 96%	Yellowing	
Hydrochloric Acid 37%	No stain	
Phosphoric Acid	No stain	
Bases		
Sodium Hydroxide 2N	No stain	
Potassium Hydroxide 2N	No stain	
Ammonium Hydroxide 29%	No stain	
Salts and Others		
Copper Sulfate	No stain	
Hydrogen Peroxide 30%	No stain	
Iron sulfate 10%	No stain	
Cobalt Sulfate	No stain	
Ferric Chloride	No stain	
Colorants		
Chromophenol Blue	Slight stain	
Brilliant Blue R	Slight stain	
Methyl Orange	No stain	
Iodine	Strong stain	
Urine		
Series 8000 times: 72 hours	No stain	

Test results were obtained by exposing samples to stains and reagents for one hour, followed

by cleaning with Azrock Neutral Cleaner.

Inlaid Commercial Vinyl Flooring																		
<i>Light Reflectance Values</i>																		
% 0-9	10-14	15-19	20-24	25-29	30-34	35-39	40-44	45-49	50-54	55-59	60-64	65-69	70-74	75-79	80-84	85-89	90-94	95-100
82002						82014 82018 82019	82003 82007 82010 82013 82021	82006 82022	82005 82017 82020	82009 83016	82001 82004 82011 82012 82015		82008					