

Vinyl Composition Tile			
	Physical Characteristics		
	Size	Gauge	Indentation resistance in pounds per sq. in.
Cortina Colors	12" x 12"	1/8" 3/32" ¹	75 75
Cortina Complement	12" x 12"	1/8"	75
Premiere	12" x 12"	1/8" 3/32"	75 75
Classic Granite	12" x 12"	1/8"	75
Thru-Quartz	12" x 12"	1/8"	75
Alvarado	12" x 12"	1/8"	75
Slip Resistant	12" x 12"	1/8"	75
Solids	12" x 12"	1/8"	75

¹In selected colors

³APA Sturd-i-floor constructed per APA Design/Construction Guide, Residential and Commercial, Form E30L revised

§ Moisture test recommended

⊠ All Azrock products should be maintained according to the recommended procedures outlined in the current Domco Installation & Maintenance Manual.

‡ For installation in areas where Azrock Slip Resistant, Luxury Vinyl Tile or Solid Vinyl Tile may be exposed to temperature changes (around freezer and refrigerator areas) and/or frequent surface water (spray from produce areas) we recommend the use of Azrock Polyurethane Adhesive

Recommended Subfloors/Adhesives				
Consult Azrock Information Manual ¹ for complete and detailed information				
Concrete, suspended	Concrete, on grade ²	Concrete, below grade ²	APA Plywood suspended	APA Sturd-i-floor³
<p>Azrock Type Z Cutback Adhesive, Azrock Black Thin Spread Adhesive, Azrock Clear Thin Spread Adhesive, Azrock Polyurethane Adhesive ‡</p>	<p>Azrock Type Z Cutback Adhesive, Azrock Black Thin Spread Adhesive, Azrock Clear Thin Spread Adhesive, Azrock Polyurethane Adhesive ‡</p>	<p>Azrock Type Z Cutback Adhesive, Azrock Black Thin Spread Adhesive, Azrock Clear Thin Spread Adhesive, Azrock Polyurethane Adhesive ‡</p>	<p>Azrock Clear Thin Spread Adhesive, Azrock Black Thin Spread Adhesive</p>	<p>Azrock Clear Thin Spread Adhesive, Azrock Black Trim Spread Adhesive</p>

Vinyl Composition Tile	Vinyl Composition Tile	
Specifications	Chemicals, Reagents, and Stains	
SS-T-312B, Interim Amendment - 1(YD), Type IV, Composition 1, asbestos-free, ASTM Designation F1066-87 Composition-1, non-asbestos formulated, (Class 1-solid color), (Class 2-through pattern), (Class 3-Alvarado), ASTM E-84 (NFPA-255) with a flame spread rating of less than 75, ASTM E-648 (NFPA-253), CRF (Critical Radiant Flux) 1.0 or more	Alcohols Denatured Alcohol Isopropyl / 70% Vol Methanol	No stain No stain No stain
	Ketones Acetone	Severe Softening
	Aldehydes Formaldehyde 37%	No stain
	Hydrocarbon Solvents Gasoline Naptha	Slight Softening No stain
	Bases Ammonium Hydroxide 30% Sodium Hydroxide 50%	No stain No stain
	Inorganic Chemicals Hydrogen Peroxide 30% Copper Sulfate 10%	No stain No stain
	Acid Reagents Acetic Acid 28% Sulphuric Acid 98% Hydrochloric Acid 38% Sulphuric Acid 10%	Bleaching, trace Bleaching, severe Bleaching, trace Bleaching, severe
	Hospital Stains, Reagents and Misc. Test Indicators Gram Stain #2 Providone-Iodine Scrub 10% Pap Stain OG-6 Hematoxylin Stain Lugol's Stock Solution	Moderate stain No stain Severe stain Slight stain Heavy stain

Sheet1

Methylene Blue	Moderate stain
Cod Liver Oil	No stain

Vinyl Composition Tile and Feature Strip									
PACKING DATA									
Description	Pieces Per Carton		Square Feet Per Carton		Approximate Pounds Per Carton		Square Meters Per Carton		Approximate Kilograms Per Carton
	3/32"	1/8"	3/32"	1/8"	3/32"	1/8"	3/32"	1/8"	1/8"
12" x 12"	45	45	45	45	48	62.5	--	4.18	28.35
1/8" SR, 12" x 12"	--	45	--	45	--	60	--	4.18	26.76
1/8" Feature Strip									
1/4" x 24"	--	100	--	200 Lin. Ft.	--	6	--	60.96 LM	2.76
1/2" x 24"	--	75	--	150 Lin. Ft.	--	9	--	45.72 LM	4.08
1" x 24"	--	50	--	100 Lin. Ft.	--	11-1/2	--	30.48 LM	5.22
2" x 24"	--	25	--	50 Lin. Ft.	--	12	--	15.24 LM	5.44
4" x 24"	--	15	--	30 Lin. Ft.	--	14	--	9.14 LM	6.35
6" x 24"	--	15	--	30 Lin. Ft.	--	21-1/2	--	9.14 LM	9.75