

MF-MATERIAL, FINISHES	
Properties Mixed and Cured	
Hardness-Shore D @ 77°F.	75
Tensile Elongation (ASTM D-638)	1-30%
Adhesion to Concrete (ACI 70-56)	>300 psi
Water Absorption (ASTM D-570)	0.8%
Heptane Resistance (ASTM D-543)	None
Extraction Absorption	0.8%

NOTE: Tensile Strength (ASTM D-638)
4,000 to 10,000 psi. Depending on System.

SEAMCO Laboratories, Inc.