

<b>FLAMESPREAD CHARACTERISTICS (ASTM E84-80)</b>					
<b>Material &amp; Substrate</b>	<b>No. of Coats</b>	<b>Rate of Application per coat/(square feet per gallon)</b>	<b>Flame Spread</b>	<b>Classification</b>	
				<b>N.F.P.A</b>	<b>U.B.C.</b>
<b>FLAMORT WC Clear, Colorless Coating</b>					
Douglas Fir	3	330	65	B	2
Southern Pine	3	225	75	B	2
Northern Hard Maple	3	225	75	B	2
Cellulose Board	3	180	50	B	2
Western Red Cedar	3	225	65	B	2
White Fir	3	225	65	B	2
Alder Battens	3	225	65	B	2
<b>FLAMORT 6-3 Clear, Colorless Coating</b>					
Douglas Fir	2	200	25	A	1

**Flamort Company 415-621-7825**